



CARBON BLACK

TECHNICAL SPECIFICATION

Physical and Chemical Properties

PROPERTIES	MÉTHOD ASTM	UNIT	SPECIFICATIONS
Iodine Number Adsorption	D-1510	mg/g	82 ± 5
Oil Absorption Number (OAN)	D-2414	cc/100mg	72 ± 5
Tintint Strength	D-3265	% ITRB	111 ± 5
Moisture	D-1509	%	1.0 Max
5' Ro- Tap Dust	D-1508	Bags	12.0 Max
		Bulk	6.0 Max
Pour Density	D-1513	Kg/g	480 ± 30
Ash	D-1506	%	0.75 Max
Sieve Residue	D-1514	35 Mesh	10 Max
		325 Mesh	200 Max
Individual Pellet Hardness	D-5230	Max	80 Max
		Average	50 Max



NEGROVEN, S.A. POSTAL MAIL 452 VALENCIA 2003, VENEZUELA

Phones.: (58-0241) 8749510 FAX: (58-0241) 8749543

e-mail: negroven@negroven.com